

Comment on “Quasiparticle Decay Effects in the Superconducting Density of States: Evidence for d-Wave Pairing in the Cuprates”

Georgios VARELOGIANNIS

Dipartimento di Fisica

Università degli studi di Roma "La Sapienza"

P.le. A.Moro 2, 00185 Roma, Italy

In a recent letter [1], D.Coffey and L.Coffey analyzed some characteristic anomalous structures in tunneling and photoemission spectra of cuprates. They concluded that the dip-like structure which appears above the gap might be considered as evidence for d-wave pairing. In the analysis of [1], this structure is due to “deviations from weak coupling mean-field behavior of the superconductivity in those materials”. While we perfectly agree with this statement, we disagree with the analysis and conclusions of [1] as well with the supposed origin of the deviations from mean-field behavior.

When quasiparticle lifetime effects become important, for the description of superconductivity it is necessary to consider a retarded strong coupling approach. The necessity of a strong coupling approach is valid even if the symmetry of the pairing is d-wave [2]. The errors in the analysis and conclusions of [1] are due to the use of a non-retarded framework, which should exclude quantitative comparison with experiment. In the case of d-wave pairing for example, the use of a retarded formalism led to the reduction of the critical temperature by an order of magnitude [2] compared to that obtained by a non-retarded approach.

The arguments advanced in [1] related with a systematic localization of the dip at 3Δ in SIS experiments are irrelevant first because Δ is not known with sufficient precision in high- T_c materials and the imprecision on the energetic position of the dip is even larger, secondly because a non-retarded approach as that used in [1] cannot give relevant quantitative information and thirdly because they disagree with the ARPES data where the dip is also observed [3].

The analysis of Ref. [1] is in fact not only quantitatively but also qualitatively contradictory to the ARPES data of the Stanford group [3] where an anisotropic gap supporting a d-wave scenario is reported. In fact within the analysis of Coffeys [1] the dip-like structure should appear in the direction where the gap is absent in a d-wave

scenario while no dip structure should appear in the direction where the gap is present. Clearly within the analysis of Ref. [1] the dip is related to the *absence* of the gap. But in the photoemission data of the Stanford group (and in all the other photoemission data) exactly the inverse happens. In the data of Ref. [3] *the dip structure appears in the direction where the gap is present while no dip appears in the direction where the gap is absent*. Therefore when arguing in support of the d-wave ideas, it is necessary to choose between Refs. [1] and [3] since they are contradictory. If the analysis of [1] is valid, then ARPES data exclude the d-wave hypothesis since no dip is seen in the direction in which the gap is absent.

Recent extensions of calculations [4] of the density of states of excitations within conventional s-wave Eliashberg theory to higher frequencies, reported an anomalous dip-like structure at temperature independent frequencies followed by a second peak or broad band [5]. Not only the form but also the temperature dependence of these last structures [5] are very similar to the experimental structures discussed in [1]. The exact frequency position (in Δ units) of the dip-like structure is coupling strength dependent [5], and could appear at 3Δ in some SIS experiments. Those structures are not associated with the characteristic frequencies of the boson mediators but are due to the breakdown of Fermi liquid picture for the virtually excited states occupied by the paired electrons because of strong electron-phonon (or other boson) coupling [5]. Within this analysis one obtain a natural explanation to the fact that the dip is more visible in ARPES experiments in the directions in which the gap is larger [6]. In addition, the recently reported asymmetry in SIN tunnel data where the dip is visible only at negative sample bias [7] excludes the analysis of Ref. [1] and can be naturally understood [6] within the s-wave strong coupling analysis [5].

The whole anomalous behavior of the density of states (finite density of states inside

the gap, anomalous T dependence of the gap, dip and second peak structures) indicates that cuprates are at the beginning of a cross-over from BCS superconductivity to Bose condensation [5]. This happens when the gap becomes comparable to the phonon energies (and this is probably the case in cuprates and fullerenes [8]), and reflects the physical constraint that the distance the paired electron covers during the absorption of the virtual phonon cannot be larger than the superconducting coherence length. The dip structure should be a characteristic of all the materials that in the analysis given in Ref. [9] of the Uemura plot, are close to the cross-over regime (high- T_c cuprates and fullerenes, heavy fermions etc.) [10].

Notice that the observation, after the publication of Ref. [1], of an analogous dip-like structure in fullerenes [9], excludes the analysis of [1], since for obvious reasons nowhere in the literature a d-wave scenario has been proposed for fullerenes. The eventual observation of the dip structure in heavy fermion compounds will further confirm the analysis of Ref. [5].

In conclusion it is obvious that the dip-like structure cannot be considered as evidence for d-wave pairing.

REFERENCES

1. D. Coffey and L. Coffey, Phys. Rev. Lett **70**, 1529 (1993)
2. P. Monthoux and D. Pines, Phys. Rev. B **47**, 6069 (1993)
3. D.S. Dessau et al., Phys. Rev. Lett. **66**, 2160 (1991)
4. P.B. Allen and D. Rainer, Nature **349**, 396 (1991)
5. G. Varelogiannis, Phys. Rev. B **51**, 1381 (1995)
6. G. Varelogiannis et al., Preprint cond-mat/9507052
7. Ch. Renner and Ø. Fischer, Phys. Rev. B **51**, 9208 (1995)
8. G. Varelogiannis, Phys. Rev. B **50**, 15974 (1994)
9. F. Pistolesi and G.C.Srtinati, Phys. Rev. B **49**, 6356 (1994)
10. G. Varelogiannis and L.Pietronero, Preprint
11. M. Knupfer et al., Phys. Rev. B **47**, 13944 (1993)